Abstract of the Disclosure

A method of forming a coupling dielectric in a memory cell includes forming an oxide on a substrate, forming Ta₂O₅ on the oxide, oxidizing the Ta₂O₅ with rapid thermal process (RTP) at a temperature above the crystallization temperature for Ta₂O₅, forming a cell nitride on the oxidized Ta₂O₅, and forming a wetgate oxide on the cell nitride.

"Express Mail" mailing label number: EV298566124US

Date of Deposit: November 19, 2003

This paper or fee is being deposited on the date indicated above with the United States Postal Service pursuant to 37 CFR 1.10, and is addressed to the Commissioner for Patents, Mail Stop Patent Application, P.O. Box 1450, Alexandria, VA 22313-1450.